

Hard Hat ConPatch

General purpose polymer-modified concrete repair mortar

DESCRIPTION

ConPatch is a general purpose polymer-modified concrete repair mortar for concrete floors, walls, precast, tilt-up and masonry surfaces. ConPatch can be used for horizontal and vertical applications to provide a durable repair that can be shaped by shaving or sanding.

FEATURES/BENEFITS

- Can be featheredged
- Repairs up to 2" in thickness
- Designed for interior & exterior repairs
- Can be shaped
- Excellent durability and adhesion
- Dries to natural concrete gray
- One component-Just add water

APPLICATION

Surface Preparation: The concrete must be sound and free of all foreign material, including oil, grease, dust, laitance or other surface contaminants. Saw cut the perimeter of the repair to a maximum depth of 1/2". Mechanically abrade the surface by an engineered approved method, such as grinding, abrasive blasting, or scarifying. All surfaces to be repaired should be in a saturated-surface-dry (SSD) condition with no standing water on the surface.

Mixing: Mix 6.75 – 7.25 pints (depending on desired consistency) of clean water per 50 pound bag of material. Mix with a low speed drill. Add recommended amount of clean water into the container, followed by the ConPatch. Mix 2 to 3 minutes. Mix only what can be applied within the setting period.

ConPatch may be used with SpecChem Acrylic Bonder neat or mixed 1 to 1 with water per 50 pounds of powder to increase durability, abrasion resistance and bond strength. The addition of Acrylic Bonder is recommended when using ConPatch in thin, small, horizontal applications subjected to heavy traffic or wear.

Bond/Scrub Coat: Use the properly

mixed ConPatch as a bond or scrub coat by scrubbing a thin layer into the pre dampened substrate with a stiff brush. Place the ConPatch mortar immediately before the bond coat dries.

Placement: Trowel ConPatch firmly into the prepared area, ensuring intimate contact with the bonding surface. Use slightly more material than is needed and roughly shape during placement. After the initial set, when ConPatch is surface hard, shave the material to the desired final shape using a steel trowel. Maximum depth of neat repair mortar is 2" for each lift. Additional lifts can be placed after the original lift has achieved set. The original lift should be left with a rough surface to improve bond between lifts.

Finishing/Curing: Finish the repair material to the desired texture to match the surrounding concrete. ConPatch is self-curing under most conditions. In severe drying conditions, use an ASTM C-309 compliant, water based SpecChem curing compound.

PACKAGING

50 lb bag
Coverage: approx 20 sq-ft @ 1/4"

STORAGE/SHELF LIFE

Shelf life of unopened bags stored in a dry facility is 12 months. Excessive temperature differential and/or high humidity can shorten the shelf life expectancy. Store in a cool, dry area away from direct sunlight.

TEST DATA

Set Time at 70°F (ASTM C-266)	
Initial Set	30 – 40 min
Final Set	60 min
Compressive Strength (ASTM C-109)	
1 day	1200 psi
7 days	5000 psi
28 days	6500 psi
Freeze-Thaw (ASTM C-672)	
Scaling Resistance	25 cycles=0% loss
Slant Shear Bond Strength (ASTM C- 882)	
14 day	1680 psi
Flexural Strength (ASTM C -348)	
28 days	650 psi
Yield	
Yield Per Bag	.43 cu-ft



13407 Yorba Ave.
Chino, CA 91710
hardhatconstructionsupply.com

Hard Hat ConPatch

General purpose polymer-modified concrete repair mortar

LIMITATIONS/PRECAUTIONS

Minimum thickness for repair is 1/8" to achieve maximum durability in heavy wear applications.

Do not retemper after initial mixing. Do not add other cements or additives to this product. ConPatch is a fast setting product, so mixing equipment should be cleaned with water as soon as possible.

Do not allow repairs to freeze until the material has reached a minimum of 1000 psi compressive strength.

In adverse temperatures, follow ACI recommendations for hot/cold weather concreting practices.

Use only potable water for mixing.

Minimum surface and ambient temperature of 45oF and rising is required at the time of application.

For optimum results, condition material to between 65 oF and 85oF.

Caution: Contains Portland Cement and sand. Cement will cause irritation. Avoid contact. A dust respirator, safety goggles, and rubber gloves are recommended.

Avoid prolonged contact with clothing.

In case of contact with eyes, immediately flush with water for at least 15 minutes.

Get prompt medical attention. Do not wear contact lenses when working with this product. DO NOT take internally.

Keep out of reach of children.

Avoid hazards by following all precautions found in the Material Safety Data Sheet (MSDS), product labels, and technical literature. Please read this information prior to using the product.

WARRANTY

NOTICE-READ CAREFULLY CONDITIONS OF SALE

The manufacturer offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of The manufacturer. No other representative of or for The manufacturer is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

The manufacturer warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, The manufacturer will replace the defective product with new product without charge to the purchaser. The manufacturer makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.



13407 Yorba Ave.
Chino, CA 91710

hardhatconstructionsupply.com