

# Hard Hat ConRock Anchoing Cement

Pourable, cement-based, non-shrinking, quick-setting anchoring cement

## DESCRIPTION

ConRock is a one-component, water-proof, non-shrinking, Portland cement-based anchoring cement that sets hard in 12-15 minutes. It expands as it sets and locks into the surrounding concrete.

## FEATURES/BENEFITS

- Quick setting; sets hard in 12-15 minutes; speeds production
- Rapid high strength up to 2000 psi. in 1 hour at 72o
- Controlled expansion as it sets
- Nonmetallic; maintains volume stability over time
- Waterproof, resistant to freeze/thaw provides durable, long-lasting applications
- Flowable, and pourable mixture; user friendly application

## APPLICATION

Recommended for use in concrete, masonry & stone for:

- Anchoring bolts
- Reinforcing rods
- Columns
- Railings
- Fences
- Bolts
- Small machines
- Hand rails
- Bridge railings
- Posts
- Signs
- Pulleys and motors

### Surface Preparation

Drill holes in sound concrete wide enough to accept the head of bolts with their washers. As a general rule the hole should be 3 times wider than the object embedded. If concrete is not sound or of questionable strength, increase the recommended drill depth indicated.

Allow sufficient hole diameter so the material will readily flow between washer and the wall of the cavity.

For added strength "mushroom" the base of the hole by tilting the drill and working it back and forth during the drilling operation.

Blow or vacuum out all loose particles

and dust, then dampen the walls of the hole with a swab to ensure a dust-free surface. Remove all standing water.

### Mixing

Mix only enough material to apply in 8 minutes and to fill the hole. Mix with clean water approx. 16.7% by weight or 1 gal/50# to a uniform, lump-free pancake-batter consistency in a small plastic bowl or other suitable container. Do not over-water the material.

## PACKAGING

50 lb (22.7 kg) pails (.43cu-ft/pail), 36 pails per pallet

## STORAGE/SHELF LIFE

18 months in pail units when properly stored and transported in unopened containers protected from moisture and dampness in a cool, clean, dry area between 45 and 90° F.

## LIMITATIONS/PRECAUTIONS

DO NOT place at temperatures below 40oF (5oC) or if the temperature is expected to fall below 40oF (5oC) in the next twenty-four hour period.

DO NOT place when temperature exceeds 90°F (32.2°C). As with all cementitious materials, avoid contact with uncoated aluminum to prevent adverse chemical reaction and possible product failure. Use treated aluminum (galvanized) or coat aluminum with an epoxy or bond coat with an acrylic bonder and ConRock.

## TYPICAL TEST DATA

Compressive Strength (ASTM C 109)	
1-hour after set	2000 psi
1 day	4650 psi
28 days	7750 psi
Expansion (ASTM C 157) moist cure = .05%	
Flexural Strength (ASTM C 78)	
28 days	1250 psi
Pull-Out Strength (NYSDOT)	
#5 Rebar, 7/8" dia hole, 6" deep	11,300 lbs

## WARRANTY

### NOTICE-READ CAREFULLY CONDITIONS OF SALE

The manufacturer offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of The manufacturer. No other representative of or for The manufacturer is authorized to grant any warranty or to waive limitation of liability set forth below.

### WARRANTY LIMITATION

The manufacturer warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, The manufacturer will replace the defective product with new product without charge to the purchaser. The manufacturer makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

### INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.



13407 Yorba Ave.  
Chino, CA 91710

hardhatconstructionsupply.com